

# PRODUCT DATA SHEET

## Avery Dennison® DOL 2800 Series

Issued: 12/2020

### Introduction

Avery Dennison DOL 2800 series are calendered laminates that have been designed as a short to medium-term protective overlaminating films for digitally printed images on flat or slightly curved substrates.

### Conversion

For processing tips and reference guides please refer to Technical Bulletins:

- » 5.3 Recommended combinations of Avery Dennison overlaminates and Avery Dennison Digital Print Media
- » 5.4 Processing tips for Avery Dennison DOL films

### Recommendations

Protective overlaminating film for digitally printed images on flat or slightly curved substrates for promotional short-term and medium-term indoor and outdoor applications.

### Features

- » Adds attractive uniform finish to a print
- » Enhances colors of image
- » Protects against UV radiation and abrasion
- » Improves durability of image (up to 3 years)



#### Face Film

75 micron flexible, transparent, calendered vinyl

DOL 2860 Promotional Gloss Clear DOL 2880 Promotional Matt Clear



#### Adhesive

Permanent, acrylic based



#### Backing

One side coated bleached kraft paper, 95 g/m<sup>2</sup>



#### Durability

3 years



#### Shelf Life

2 years

## Physical Characteristics

	Test method <sup>1</sup>	Results
<b>Product</b>		
Caliper, facefilm (micron)	ISO 534	80
Caliper, facefilm + adhesive (micron)	ISO 534	100
Gloss (GU)		
DOL 2860 Promotional Gloss Clear	ISO 2813, 20°	70
DOL 2880 Promotional Matt Clear	ISO 2813, 85°	75
Shelf life (years)	Stored at 22° C/50-55 % RH	2
Durability <sup>2</sup> (years)	Vertical exposure	3
Fire Classification Rating	EN 13501-1	B-s1, d0
<b>Adhesive</b>		
Adhesion, initial (N/m)	FINAT FTM-1, stainless steel	440
Adhesion, after 24 hours (N/m)	FINAT FTM-1, stainless steel	580
<b>Temperature range</b>		
Application temperature (min °C)		see TB 5.4
Service temperature (°C to +°C)		-40 - +80
<b>Chemical properties<sup>3</sup></b>		
Chemical resistance	Mild acids	No effect
Solvent resistance	Mild alkalis	No effect
Solvent resistance	Applied to aluminium	No effect exposed to: oils, greases, aliphatic solvents, motor oils, heptane, kerosene and JP-4 fuel.

## Important

Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.

1) Test methods: More information about our test methods can be found on our website.

2) Durability: The durability is based on middle European exposure conditions. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing south; in areas of long high temperature exposure such as southern European countries; in industrially polluted areas or high altitudes, exterior performance will be decreased.

3) Prolonged immersion in gasoline and similar fluids is not recommended.

*Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>.*

*Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.*

© 2020 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.