

DirectTex®

Softimage Contrast

Fields of application

.01 .02 .03 .04 .07

Specifications



REF. 599150 150



100 % polyester



ca. 160/ 252/ 320/ 505 cm
ca. 63/ 99/ 126/ 199 inch
other widths available on request



B-s1, d0 DIN EN 13501-1



ca. 210 g/m²
ca. 6.8 oz/yd²



ca. 0.37mm
ca. 370 µm



rolls
100 m
109 yd



length: 448.7 N
cross: 683.6 N
DIN EN ISO 13934-1



length: 31.4 %
cross: 53.3 %
DIN EN ISO 13934-1



blank: 7
DIN EN ISO 105-B02



blank: 88.76
DIN 5033-1



length: 0.9 %
cross: 0.7 %
DIN EN 14704-1



cold, ultrasonic cut

Printing methods

print	UV	Latex	Dyesub
Inside	•		•
Outside			

Article shrinkage (50 sec hold up time)

	shrinkage in cross direction	shrinkage in longitudinal direction	recommended fixing temperature
180°C	0,5 %	1,2 %	185
190°C	/ %	/ %	
200°C	/ %	/ %	
210°C	/ %	/ %	

Certifications



DirectTex® Softimage Contrast

Fields of application

.01 .02 .03 .04 .07



Ref.-Nr.: 599150 150 | Preview print sample